
RG 104, 8NS-104-94-077 Box 6

8NS-104-94-077, Miscellaneous Correspondence & Memos, 1897-1994



Government Honduras	No. Plucos 5,000,000
Date order received May 25, 1972	Was and the Country NO
batt order received May 23, 1972	Was master die furnished No
Mint where coined Denver	Was master die returned
Denomination 5 Centavo	Number melts made 226
Date coinage started 8-2-72	No, melts delivered to Coiner
Date coinage completed 9-5-72	Ounces per melt
Cost per M	No. ingots per melt
Alloy 75 cu 25 Ni.	Weight per ingot
Weight per coin 5 grams	Size of ingot
Weight tolerance	Assay passing tol. on ingot
Fineness Tol.	Diameter of cut blank830
Diameter827 Tol.	Thickness of cut blank .0645
Thickness .079 Tol.	Diameter of upset blank820
Reeded edge	Edge thickness upset blank 077
Plain edge Yes	Pieces cut across strip
Lettered edge	Pieces cut at one stroke
Wastage allowed per M	Annealing temperature 1450
Turn - standard or medal Standard	% rejects, automatic scales
Year (dated) 1972	% rejects if reviewed
fint mark No	% good coins from ingots
Vas sample coin submitted Yes	No. pieces per bag5,000
Vas sample strike approved	Weight tol., M pieces
ie average obv. and Date shipped 9-5	5-72
Remarks: Used nickel (U.S.) blanking of	lie set and U.S. nickel press

Remarks: Used nickel (U.S.) blanking die set and U.S. nickel press setup. Used 1 conventional press. Upset blanks in a U.S. quatter groove. No problems. Used anaconda strip and replaced the strip with weight per coin same as U.S. nickel. Used H.M.E. press for a day or two on Honduras centavos.

UNITED STATES GOVERNMENT

Memorandum

TO

Superintendents of Melting, Coining, Cash, Assay and Mechanical Divisions

DATE:

August 8, 1973

Cost Accounting Branch

SUBJECT:

Job Numbers for Honduras 50 Centavo - 92,000 Pounds of Cu. Ni. Strip

Melting:

_	Dept.	Charge	Denomination
	7700	7767	Ingot
Process Weigh:			
••	8100	8167	
Rolling:			
	7900	7967	Strip
Material Handling:	,		
	7800	7967 -3 7967 -1	Strip Preparation of Shipment
Assay:			
	3500	7767	Ingot
Mechanical Divisio	n:		
	6000	7967	Strip, etc.

'oun-

OPTIONAL FORM NO. 10 MAY 1962 EDITION GSA FPMR (41 CFR) 101-11.8

UNITED STATES GOVERNMENT

Memorandum

96 onduras

TO : Superintendent's of Melting, Coining, Assay,

Cash & Deposits and Mechanical Divisions

DATE: June 29, 1972

FROM :

Cost Accounting Branch

SUBJECT: Job Numbers for 5 Centavo, Honduras Coins

MA		•	1 23	
Me	-	•	-	M.

	Dept.	Charge	Denomination
	7700	7770	Ingot
Process Weigh			
/	8100	8170	5¢ Centavo
Rolling (Includes	Slab Anneali	ng)	
	7900	7970	5¢ Centavo
Material Handling	4	1	
	7800	7870-3 7870-4	5 Centavo Strip 5 Centavo Scrap
/		7870-2	Ingots
Blanking			
	8200	8270	5 Centavo
Annealing			
	8300	8370	5 Centavo
Upsetting		5/14	
	8500	8570	5 Centavo
Selecting			
	8800	8870	5 Centavo
Stamping			
	8600	8670*	5 Centavo



Memorandum - (Continued)

Job Numbers for 5 Centavo, Honduras Coins

Counting

Codifering			
	Dept.	Charge	Denomination
	8700	8770	5 Centavo
Stores Items		8770	5 Centavo Bags
Cash and Deposit	8		
Labor	1300	1370	Preparation of Shipment
Stores Items Labor	1300	1370 1371 1372	5 Centavo Boxes 5 Centavo (Boxing Bags & Banding Boxes) Skids, Band, and Seals
Assay		1	
	3500	7770	5 Centavo Ingot
Mechanical Divis	sion		
字 大大大大学 5.3%	Dept.	Charge	Job Request
	6000	6010 8574 8674 8274	6631 - Collars (Segments and Discs) (Grinding and Dies) (Sharpening Die Sets)

7-6-72 Norduras 5 Centavo 75 % nof 25 % Cu. Cut Blank Pia = ,828 Thickmen ,064 opp. 5 millson for 1 account # 8270 Punching account # 7970 Rolling & Slitting app-230 Ingoto.

Beston

Nay 19, 1972

RECEIVED

MAY 25 1972

Mr. Micholae G. Theodore
Superintendent
United States Mint
Independence Mall
Philodolphia, Pennsylvania 19106

SUPERINTENDENT
U. S. MINT AT DENVER

Donr Mr. Theodore:

We have been requested to manufacture 5 million 5-Centavo coins for the Government of Monduras. This order will be produced at the Denver Mint. The specifications are as follows:

	ALLOY	PEIGHT	DIMPETER	THICKNESS
Cut Blank	75 Cu - 25 71.	5 Grams	.840" 840	.052".06
Upset Blank	75 Cu - 25 Ni.	5 Grams	.820" 810	
Coin	75 Cu - 25 Ni.	5 Grams	.827" 827	

The coin has a plain edge.

You are requested to proceed with the change of date on the master die. The date should be changed to 1972. In addition, you are authorized to manufacture dies, collars, blanks, and upsatting segment as may be required for trial striking of this coin. You should plan to have sufficient waterial to make the following dietribution of specimens:

		le hollow to	BLANKS.	
		COIN	CUT UPSET	
Eures	u ·	. 2	0 0	
Denve		2	2 2	*
Hondu	TAS .	2	0 0	

Please advise this office when work has progressed to the point where a trial strike can be scheduled.

Coming Com M. Color M

By copy of this letter, the Denver Hint is authorized to proced with the production of the approximately 80,000 pounds of 75 Cu - 25 Mi strip required for this order. You should place your order for working dies as soon as possible. Since the coin has a plain adge, it is expected that you will make your own collars.

Wonduran has requested that the coins be packaged 5.000 per box. Two bags per box. The boxes are to be bonded with steel strapping and placed on skids. Wenduras desires that the bags and boxes be marked "B C DE H." We are attempting to determine if any additional labeling as to value and denomination will be required.

Sincerely,

(Signed) F. H. MacDonald

Mary Brooks Director of the Mint

cc: Caperintendent, US. Mint, Denver, Colorado

A.J. Goldman --

S.F. Carwile

G.G. Ambrose

RECEIVED

MAY 25 1972

OFFICE OF
SUPERINTENDENT
U. S. MINT AT DENVER

UNITED STATES GOVERNMENT

Memorandum

TO: Rolling & Culling Branch DATE: 10/30/73

FROM: Conneg Office

SUBJECT: Honduras strip finish. .054"+.0011/2 = 50 Centano -

W. Summers!



Buy U.S. Savings Bonds Regularly on the Payroll Savings Plan

5-CENT.	Avo- Hone	OURHS	NIX ALLOY
PASS	DINL	GAUGE	X-RHY
/	225	,190	
	A	NNEAL.	
2	185	147	
3	150	115	
4	130	.090	
5	125	.072 SE	Lect 115
6	120		098 -
EDGE,060	570,064	wt. Din	840
	50 CENT	TAVO- HONOUR	NIX-ALLOY
Rea @ 220 -		6	X-RAY
PHSS	D1186	GAUGE	
/	225		
		NNERL	
2.	185	, 147	
3	150	. 115	
4	130	.090	
. 3	120	.072	
6.	113	, 063	SELFET - 098
7	107	.05400	15 084.
EDGE ,0525	- CENTER	.0545	STRIP-ONLY

200

.

